

各国孔径、目数对照表

目数	孔径 mm				法国		日本	
	中国	美国	英国	德国	NO(筛号)	孔径mm	目数	孔径mm
3.5		5.6		5	38	5	3.5	5.6
4	4.75	4.75		4	37	4	4	4.75
5	4	4	3.35	3.15			4.7	4
6	3.2	3.35	2.8		36	3.15	5.5	3.35
7		2.8	2.36	2.5	35	2.5		
8	2.5	2.36	2				7.5	2.36
10	2	2	1.7	2	34	2	10	1.7
12	1.6	1.7	1.4	1.6	33	1.6	12	1.4
14	1.43	1.4	1.18				14	1.18
16	1.25	1.18	1	1.25	32	1.25	16	1
18	1	1	0.85	1	31	1	18	0.85
20	0.9	0.85	22目0.71				22	0.71
24	0.8	25目0.71	25目0.6	0.8	30	0.8		0
26	0.71						26	0.6
28	0.63			0.63	29	0.63		
30	0.6	0.6	0.5					
32	0.56							
35	0.5	0.5	36目0.425	0.5	28	0.5	36	0.425
40	0.45	0.425					42	0.355
45	0.4	0.355	44目0.355	0.4	27	0.4		
50	0.355	0.3	52目0.3				50	0.3
55	0.315			0.315	26	0.315		
60	0.3	0.25	0.25				60	0.25
65	0.25			0.25	25	0.25		
70	0.22	0.212	72目0.212				70	0.212
75	0.21			0.2	24	0.2	74	0.2
80	0.2	0.18					83	0.18
85	0.18		0.18		23	0.16		
90	0.17			0.16			93	0.16
100	0.15	0.15	0.15				100	0.15
120	0.125	0.125	0.125	0.125	22	0.125	119	0.125
150	0.1	140目0.106	0.106	0.1	21	0.1	149	0.1
180	0.088	170目0.090	170目0.090	0.09	20	0.08	166	0.09
200	0.074	0.075	0.075	0.071			200	0.075
260	0.057	270目0.063	240目0.063	0.056	19	0.063	235	0.063
300	0.05	0.053			18	0.05		
325	0.045	0.045		0.045	17	0.04	330	0.045
400	0.038	0.038	403目0.045				390	0.038
备注	试验筛	ASTM-E11	B. S410	DIN4183	Afiior1938		JISZ-8801-1992	